

BENTOFIX[®] SRNWL

Formerly known as NWL

Thermal Lock[®] Geosynthetic Clay Liners

Bentofix Thermal Lock[®] SRNWL Series Geosynthetic Clay Liner (GCL) is a needlepunched, thermally reinforced composite comprised of a core of natural Wyoming sodium bentonite clay between two durable geotextile layers to form a low permeability hydraulic barrier. The top layer is a staple fiber nonwoven (NW) geotextile while the bottom layer is a scrim reinforced nonwoven (SRNWL) geotextile. The product is intended for moderate to steep slopes and moderate to high load applications where increased internal shear strength is required. Product intended where subgrade conditions are rough in nature, prevent shrinkage below geomembranes, and/or where hydraulic head conditions may apply.

Property	ASTM Test Method	Frequency	Value Imperial Units	Value Metric Units
Typical Geotextile Properties				
• Top / Cap Nonwoven	D 5261	200,000 sq ft	6.0 oz./yd ² MARV	200 g / m ² MARV ⁽¹⁾
• Scrim Reinforced Nonwoven Bottom Fabric	D 5261	(20,000 m ²)	6.0 oz./yd ² MARV	200 g / m ² MARV
Bentonite Properties (SI Units Only)				
• Swell Index	D 5890	100,000 lbs.	24 ml/ 2 g min	24 ml/ 2 g min
• Moisture Content	D 4643	(50,000 kg)	12 % max	12 % max
• Fluid Loss	D 5891	100,000 lbs.	18 ml max	18 ml max
• Smectite (Montmorillonite)	XRD	Periodic	90% min	90% min
Finished GCL Properties				
• Bentonite Mass/Unit Area ²	D 5993	40,000 ft ² (4,000 m ²)	0.75 lbs/ft ² MARV	3.66 kg/m ² MARV
• Tensile Strength ³	D 6768	40,000 ft ² (4,000 m ²)	50 lb/in MARV	8.8 kN/m MARV
• Peel Strength	D 6496	40,000 ft ² (4,000 m ²)	3.5 lbs/in min	610 N/m min
• Permeability ⁵	D 5887	Weekly	5 x 10 ⁻⁹ cm/s max	5 x 10 ⁻⁹ cm/s max
• Index Flux ⁵	D 5887	Weekly	1 x 10 ⁻⁸ m ³ /m ² /s max	1 x 10 ⁻⁸ m ³ /m ² /s max
• Internal Shear Strength ⁶	D 6243	Periodic	500 psf Typical	24 kPa Typical

(1) Minimum Average Roll Value.

(2) Oven-dried measurement. Equates to 0.84 lb/sqft (4.1 kg/sqm) when indexed to 12% moisture content.

(3) Tested in machine direction.

(4) Modified ASTM D4632 to use a 4 in (100mm) wide grip. The maximum peak of five specimens averaged in machine direction.

(5) Deaired, deionized water @ 5 psi (34.5 kPa) maximum effective confining stress and 2 psi (13.8 kPa) head pressure.

(6) Typical peak value for specimen hydrated for 24 hours and sheared under a 200 psf (9.6 kPa) normal stress.