

Terrafix 800R - Geotextile

Function: Filtration, Drainage, Reinforcement & Cushion.

Terrafix 800R is a needle-punched nonwoven geotextile made of 100% virgin polypropylene staple fibers, which are formed into a random network for dimensional stability. Terrafix 800R resists ultraviolet deterioration, rotting, biological degradation, naturally encountered alkalis and acids. Polypropylene is stable within the pH range of 2-13.

Types of applications for 800R are: Light Coastal Applications / Abrasion Resistance Requirements / Cushion Requirements as well for plastic liners to avoid punctures in a plastic liner such as EPDM, PVC, HDPE.

800R: 24" (inches) maximum rip-rap size / Good abrasion resistance / Medium to high strength at high elongation.

Property	ASTM Test Method	Value Metric Units
Typical Geotextile Properties		
• Grab Tensile Strength	D 4632	1330 N
• Tear Resistance	D 4533	500N
• Grab Elongation	D 4632	50%
• Puncture CBR	D 6241	3780 N
• Permittivity	D 4491	1.0 sec ⁻¹
• Water Flow	D 4491	3055 l/min/m ²
• Apparent Opening Size	D 4751	0.150 mm
• U.V. Stability	D 4355	70% @ 500hrs

The information contained herein has been compiled by TAG Ltd. and is, to the best of our knowledge, true and accurate. This information is offered without warranty. Final determination of suitability for use contemplated is the sole responsibility of the user. This information is subject to change without notice. Terrafix is a registered trademark of Terrafix Geosynthetics Inc. Terrafix 03-2018.