

## **BENTOFIX® SRNWL**

*Also known as NW*

### **Thermal Lock® Geosynthetic Clay Liners**

Bentofix Thermal Lock® SRNWL Series Geosynthetic Clay Liner (GCL) is a needlepunched, thermally reinforced composite comprised of a core of natural Wyoming sodium bentonite clay between two durable geotextile layers to form a low permeability hydraulic barrier. The top layer is a staple fiber nonwoven (NW) geotextile while the bottom layer is a scrim (woven) reinforced nonwoven (SRNW) geotextile. The product is intended for moderate to steep slopes and moderate to high load applications where increased internal shear strength is required. Product intended where subgrade conditions are rough in nature, prevent shrinkage below geomembranes, and/or where hydraulic head conditions may apply.

Property	ASTM Test Method	Frequency	Value Imperial Units	Value Metric Units
<b>Typical Geotextile Properties</b>				
• Top / Cap Nonwoven (NW)	D 5261	200,000 sq ft	6.0 oz./yd <sup>2</sup> MARV	200 g / m <sup>2</sup> MARV <sup>(1)</sup>
• Scrim Reinforced Nonwoven Bottom Fabric (SRNW)	D 5261	( 20,000 m <sup>2</sup> )	6.0 oz./yd <sup>2</sup> MARV	200 g / m <sup>2</sup> MARV
<b>Bentonite Properties</b> (SI Units Only)				
• Swell Index	D 5890	100,000 lbs.	24 ml/ 2 g min	24 ml/ 2 g min
• Moisture Content	D 4643	(50,000 kg)	12 % max	12 % max
• Fluid Loss	D 5891	100,000 lbs.	18 ml max	18 ml max
<b>Finished GCL Properties</b>				
• Bentonite Mass/Unit Area <sup>2</sup>	D 5993	40,000 ft <sup>2</sup> (4,000 m <sup>2</sup> )	0.75 lbs/ft <sup>2</sup> MARV	3.66 kg/m <sup>2</sup> MARV
• Tensile Strength	D 6768	40,000 ft <sup>2</sup> (4,000 m <sup>2</sup> )	50 lb/in MARV	8.8 kN/m MARV
• Peel Strength	D 6496	40,000 ft <sup>2</sup> (4,000 m <sup>2</sup> )	3.5 lbs/in min	610 N/m min
• Permeability <sup>3</sup>	D 5887	Weekly	5 x 10 <sup>-9</sup> cm/s max	5 x 10 <sup>-9</sup> cm/s max
• Index Flux <sup>3</sup>	D 5887	Weekly	1 x 10 <sup>-8</sup> m <sup>3</sup> /m <sup>2</sup> /s max	1 x 10 <sup>-8</sup> m <sup>3</sup> /m <sup>2</sup> /s max
• Internal Shear Strength <sup>4</sup>	D 6243	Periodic	500 psf Typical	24 kPa Typical

(1) Minimum Average Roll Value.

(2) Oven-dried measurement. Equates to 0.84 lb/sqft (4.1 kg/sqm) when indexed to 12% moisture content.

(3) Deaired, deionized water @ 5 psi (34.5 kPa) maximum effective confining stress and 2 psi (13.8 kPa) head pressure.

(4) Typical peak value for specimen hydrated for 24 hours and sheared under a 200 psf (9.6 kPa) normal stress.

The information contained herein has been compiled by TAG Ltd. and is, to the best of our knowledge, true and accurate. This information is offered without warranty. Final determination of suitability for use contemplated is the sole responsibility of the user. This information is subject to change without notice. TAG is a division of Terrafix Geosynthetics Inc. GCLs since 1992. 04-2021.