

Terrafix TTX130S

TTX130S is a polypropylene single layer extruded in a three-dimensional direction. This engineered geogrid is stabilized to resist degradation due to ultraviolet exposure. It is resistant to commonly encountered soil chemicals, mildew, and insects, and is non-biodegradable. Polypropylene is stable within a pH range of 2 to 13, making it one of the most stable polymers available for geogrids today. TTX130S is manufactured to meet the following minimum average roll values:

PROPERTY	TEST METHOD	Longitudinal	Diagonal	General
Index Properties				
Rib pitch, mm (in)	ASTM D4759	33 (1.30)	33 (1.30)	
Mid-rib depth, mm (in)	ASTM D4759			
Mid-rib width, mm (in)	ASTM D4759			
Rib Shape	ASTM D4759			Rectangular
Aperture shape	ASTM D4759			Triangular
Mechanical properties				
Radial Stiffness at 0.5% strain (kN/m)	ASTM D7737-11			200
Radial Stiffness at 2.0 strain (kN/m)	ASTM D7737-11			140
Radial Stiffness Ratio	ASTM D6637			0.6
Juction Efficiency %	ASTM D7737			93
Resistance to Chemical Degradation	EPA 9090			100%
Resistance to UV Degradation	ASTM D4355			70 % @ 500 hrs

1. At the time of manufacturing. Handling, storage, and shipping may change these properties.
2. Value represents maximum average roll value.

Index Properties:

Geogrid testing values in accordance with ASTM D4759 (minimum average roll values) in accordance with test methods EOTA TR041 and ISO 10319 at the temperature of 21±1°C.

Mechanical properties:

*ASTM D6637-10 and ASTM D7737-11: Junction efficiency %. Load transfer capability is determined as a percentage of ultimate tensile strength.

**ASTM D6637-10: radial stiffness at low strain, kN/m @ 0.5% strain (lb/ft @ 0.5% strain). Radial stiffness is determined from tensile stiffness measured in any in-plane axis. Stiffness Ratio: The ratio between the minimum and maximum observed values of radial stiffness at 0.5% strain, measured on rib and midway between rib directions.

***EPA 9090: Resistance to chemical degradation. Resistance to loss of load capacity or structural integrity when subjected to chemically aggressive environments including acids, alkalis and salts, normally found in soils. Also, it is not a nutrient, therefore, these products will not be affected by micro-organisms in soil.

****ASTM D4355-05: Resistance to ultra-violet light and weathering. Resistance to loss of load capacity or structural integrity when subjected to 500 hours of ultraviolet light and aggressive weathering.

DISCLAIMER: Descriptions regarding the products described herein are based solely upon information provided by the manufacturer and are provided for informational purposes only. **NOTHING CONTAINED HEREIN SHOULD BE CONSTRUED AS CREATING AN EXPRESSED OR IMPLIED WARRANTY, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS, EACH OF WHICH IS HEREBY DISCLAIMED. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF.** The final determination as to the suitability of any product of Terrafix Geosynthetics Inc. in any particular application rests solely with the user. Terrafix Geosynthetics Inc. reserves the right to alter or modify its products and descriptions at any time without notice.

2023/01/09