

Physical Properties
Ground Cover Specifications

Property	Standard	Unit	HC-108gsm
Weight	ASTM D5261	OZ / SY	3.2
Grab Strength - MD	ASTM D4632	N / LB	645 N / 144.98 LB
Grab Strength - CD	ASTM D4632	N / LB	612 N / 137.56 LB
Grab Elongation	ASTM D4632	%	23.15
UV Stability (@ 500 hours)	ASTM D4533	%	90%
UV Stability (@ 1000 hours)	ASTM D4533	%	85%
UV Stability (@ 2500 hours)	ASTM D4533	%	72%

(1) Max. Average roll values
(2) UV resistance : 80% 500hr.