

Property	Unit of Measure	Typical Value	Test Method
Weight	gsm	39.2	WSP 130.1
Elongation			
MD	%	69.2	WSP 110.4
CD		68.4	
Tensile			
MD	N/5cm	99.0	WSP 110.4
CD		60.7	

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. Except when agreed to in writing for specific conditions of use, no warranty or guarantee expressed or implied is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent. This information reflects typical properties and should not be considered as specifications.