

Siltsack (Catch Basin Inlet Filter / Hi - Flow) Fabric Data Sheet

Property	Test Method	Geotech
Grab Tensile	ASTM D4632	250 x 270 lbs
Grab Elongation	ASTM D4632	20% x 20%
Mullen Burst	ASTM D3786	400 psi
Puncture	ASTM D4833	130 lbs
CBR Puncture	ASTM D6241	850 lbs
Trapezoid Tear	ASTM D4533	90 lbs
UV Resistance	ASTM D4355	200hr 70%
AOS ¹	ASTM D4751	20sieve ^(*1)
Permittivity	ASTM D4491	1.5 sec. ⁻¹
Flow Rate	ASTM D4491	180 gal/min/ft ²

*The numerical values indicate minimum average roll value (MARV)