

TGC3030-4 *Biaxial Composite Geogrid*

Terrafix TGC3030 is a Polypropylene Monolithic Extruded Biaxial Geogrid bonded with a non-woven geotextile, resulting in a geogrid that provides separation, filtration, interaction, confinement, and reinforcement. Used as an effective base reinforcement and subgrade improvement, Terrafix TGC3030 is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids. Polypropylene is stable within a pH range of 2 to 13.

Property	ASTM Test Method	Machine Direction Strength (MD)	Cross Machine Direction Strength (XMD)
Geogrid Mechanical Properties			
• Ultimate Tensile Strength ⁽²⁾	D 6637	30.0 kN/m	30.0 kN/m
• Junction Strength ⁽²⁾	GRI-GG2	37.2 kN/m	37.2 kN/m
• Junction Efficiency	%	95%	95%
• Tensile Strength @ 2% Strain ⁽²⁾	D 6637	10.5 kN/m	10.5 kN/m
• Tensile Strength @ 5% Strain ⁽²⁾	D 6637	21.0 kN/m	21.0 kN/m
• Flexural Stiffness/Rigidity	D 7748	2,000,000 mg-cm	2,000,000 mg-cm
• Radial Stiffness @0.5% Strain	D 6637	41,000 lb/ft /	600 kN/m
• Aperture Stability ⁽¹⁾	COE	0.75 M-N/deg. @ 20kg-cm torque	
Geotextile Physical Properties			
• Mass per unit area	D 5261	150 g/m²	
• Ultimate Tensile Strength	D 4595	11 kN/m	
• Tensile Elongation	D 4595	45%	
• CBR Puncture Strength	D 6241	1800N	
• Apparent Opening Size	D 4751	0.11mm	

Roll Properties

• Aperture Size	--	34mm (±1mm)	34mm (±1mm)
• Average Rib Thickness	D1777	2.5mm	1.5mm
• Roll Size	--	50m	3.90m

Typical Geogrid Properties

• Minimum Carbon Black Content	D 4218	2%	2%
• Resistance to UV Degradation	D 4355	100%	

⁽¹⁾ In-plane torsional rigidity measured by applying a moment to the central junction of a 225mm x 225mm specimen restrained at its perimeter in accordance with U.S. Army Corps of Engineers Methodology for measurement of Torsional Rigidity (Kinney, T.C. Aperture Stability Modulus ref 3, 3.1.2000)

⁽²⁾ Values shown are MARV as per GRI.